

Typical mix design

	Pieri® DRC Grade	Fine aggregate 0-2 to 0-4 mm	Coarse aggregate 1 4-8 to 6-10 mm	Coarse aggregate 2 8-12, 15-25 to 20-40 mm		
Continuous curve	6/01	700 to 800 kg	1100 to 1000 kg	Crushed aggregate	Crushed aggregate	
			800 to 900 kg			
	6/02 6/10 6/25	600 kg	600 kg			200 to 300 kg
			600 kg			600 kg
6/50	600 kg	600 to 500 kg	Crushed or rounded aggregate	600 to 700 kg		
Discontinuous curve	6/80	600 kg	0 kg	Crushed or rounded aggregate	Crushed or rounded aggregate	
	6/100					1200 kg
	6/130 6/200 6/300	600 to 500 kg				1300 to 1200 kg